



US006415486B1

(12) **United States Patent**
Prevey, III

(10) **Patent No.:** US 6,415,486 B1
(45) **Date of Patent:** Jul. 9, 2002

(54) **METHOD AND APPARATUS FOR PROVIDING A RESIDUAL STRESS DISTRIBUTION IN THE SURFACE OF A PART**

FR 2662623 * 12/1991
JP 62-292362 * 12/1987 29/90.01
ZA 8103064 * 3/1982

OTHER PUBLICATIONS

- (75) Inventor: **Paul S. Prevey, III**, Cincinnati, OH (US)
- (73) Assignee: **Surface Technology Holdings, Ltd.**, Cincinnati, OH (US)
- (*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

Classification of Metal-Burnishing Methods and Tools, by Yu. G. Schneider, *Machines and Tooling*, vol. XL, No. 1 pp. 35-39 (1969).

Statistical Analysis of the Effects of Ball Burnishing Parameters on Surface Hardness, by N.H. Loh, S.C. Tam, B. Miyazawa, Elsevier Sequola (1988).

Wear, by M. Fattouh, M.H. Blaxir and S.M. Serage, Elsevier Sequola, vol. 127, pp. 123-127 (1988).

The Measurements of Subsurface Residual Stress and Cold Working Distributions in Nickel Base Alloys, by Paul S. Prevey, Pub. ASM Conference Proceedings (1987).

Tools For Roller Burnishing, Deep Rolling, Forming, Pub. by Cogsdill Tool Products, Inc. (1996).

- (21) Appl. No.: **09/516,328**
- (22) Filed: **Mar. 1, 2000**
- (51) **Int. Cl.⁷** **B24B 39/00**
- (52) **U.S. Cl.** **29/90.01; 72/75; 72/377**
- (58) **Field of Search** **29/90.01; 148/903; 72/75, 377**

* cited by examiner

(56) **References Cited**

U.S. PATENT DOCUMENTS

1,784,866 A	* 12/1930	Fahrenwald	29/90
3,494,013 A	2/1970	Gottschald	29/90
3,770,595 A	11/1973	Gros et al.	204/29
3,820,210 A	6/1974	Kalen	29/90
4,118,846 A	10/1978	Korte	29/90
4,132,098 A	1/1979	Culver et al.	72/102
4,509,351 A	4/1985	Rolin et al.	72/19
4,565,081 A	1/1986	Massee	72/19
4,821,388 A	4/1989	Okumura et al.	29/159.01
4,947,668 A	8/1990	Ostertag	72/75
5,099,558 A	3/1992	Wilson	29/90.01
5,329,684 A	7/1994	Budet et al.	29/90.01
5,522,706 A	6/1996	Mannava et al.	416/215
5,525,429 A	6/1996	Mannava et al.	428/610
5,666,841 A	9/1997	Seeger et al.	72/110
5,826,453 A	10/1998	Prevey, III	72/75

Primary Examiner—S. Thomas Hughes

Assistant Examiner—Eric Compton

(74) *Attorney, Agent, or Firm*—Mark F. Smith; Smith, Gutttag, Hasse & Nesbitt Ltd.


FOREIGN PATENT DOCUMENTS

EP 0041248 * 12/1981 29/90.01

(57) **ABSTRACT**

The present invention is a novel method and an apparatus for implementing the method of inducing a layer of compressive residual stress along the surface of a part comprising the steps of selecting a region of the part to be treated; selecting the magnitude of compression and the residual stress distribution to be induced in the surface of the selected region of the part; exerting pressure against the surface of the selected region, the pressure being applied in a selected pattern along the surface to form zones of deformation having a deep layer of compressive stress; and varying the pressure being exerted against the surface to produce the desired residual stress distribution and magnitude of compression within the surface.

19 Claims, 9 Drawing Sheets






Fig. 1





Fig. 2



Depth ($\times 10^{-3}$ mm)

Fig. 3




Fig. 4A




Fig. 4C

Fig. 4B




Fig. 5A




Fig. 5B




Fig. 6A




Fig. 6B




Fig. 7




Fig. 8




Fig. 9







Fig. 10






Fig. 14

1

**METHOD AND APPARATUS FOR
PROVIDING A RESIDUAL STRESS
DISTRIBUTION IN THE SURFACE OF A
PART**

RELATED PATENT APPLICATIONS

The present Application deals with related subject matter in co-pending U.S. patent application entitled METHOD FOR REDUCING TENSILE STRESS ZONES IN THE SURFACE A PART, filed on the same day as the present application and having the same inventor in common.

BACKGROUND OF THE INVENTION

This invention relates to a method and an apparatus for imparting residual stress in the surface of a part and, more particularly, to a method of inducing a selected compressive residual stress distribution within the surface of a part to improve fatigue and stress corrosion performance of the part and an apparatus for implementing the method. Surface residual stresses are known to have a major effect upon the fatigue and stress corrosion performance of component parts. Tensile residual stresses, which can develop during manufacturing processes such as grinding, turning, or welding are well known to reduce both fatigue life and increase sensitivity to corrosion-fatigue and stress corrosion cracking of the part. Further, many parts that are subjected to high dynamic stresses or have areas where stress concentrations occur, such as blades and the rotor disks of turbo machinery, are prone to crack initiation and relatively rapid crack growth. The blades typically comprise an airfoil portion, a platform for partially defining a surface for fluid flow there over when the blade is mounted to the rotor disk, and a root portion having retention grooves which engage in corresponding axially extending complementary grooves of the disk. During engine operation, the rotor disk and the blade are subjected to large centrifugal loads that produce high dynamic stresses that may cause high cycle fatigue along portions of the rotor disk and the blade causing cracking and possible failure of the part. Further, the leading edge of the airfoil is often subjected to damage caused by the impact of foreign objects in the fluid stream. Such impact often results in cracks forming along the leading edge that may result in failure of the blade.

It is well known that compressive residual stresses induced in the surface of a part can increase fatigue life and reduce susceptibility to corrosion-fatigue and stress corrosion cracking. There are currently several methods used in industry for inducing compressive stress in the surface of a metal part and the particular method selected has been dependent on factors such as the dimensions and shape of the part, its strength and stiffness, the desired quality of the finished surface, the desired physical properties of the finished part, and the expense of performing the operation.

One method commonly used in industry to induce compressive stress in the surface of a part is shot peening, whereby a plurality of metallic or ceramic pellets are projected mechanically or through air pressure to impinge the surface of the part. While such a method is relatively inexpensive and is preferred for many applications, shot peening is unacceptable for parts requiring a superior finish or requiring a greater depth of compressive stress penetration and has also been found to be unacceptable for parts requiring localized or well defined compressive stress regions. Further, for parts such as a rotor disk for use in turbo machinery, the bore surfaces of the rotor disk are subjected to low levels of plastic strain (typically between about 0.2%

2

to about 0.5%) when the rotor disk is accelerated to full speed. If the surfaces have been highly cold worked, such as during shot peening, the cold worked compressive surface material will not yield in tension while the lower yield strength interior material will yield during engine operation. On unloading, such as when the rotor speed is reduced, the surface is driven into tension and will remain in tension, reducing its fatigue life, for the remaining life of the component.

Another method commonly used in industry to induce compressive stress in the surface of a part is laser shock peening, whereby multiple radiation pulses from high power pulsed lasers produce shock waves on the surface of the part to produce a high magnitude localized compressive stress within a particular region. Unfortunately, however, laser shock peening is relatively expensive and time consuming making it unacceptable for many applications.

A method which have been developed and is widely used in industry to improve surface finish, fatigue life, and corrosion resistance by deforming the surface of a part is burnishing whereby a rotary or sliding burnishing member is pressed against the surface of the part in order to compress the microscopic peaks in the surface into adjacent hollows. Burnishing operates to develop compressive stresses within the part by yielding the surface in tension so that it returns to a state of compression following deformation.

The burnishing apparatus utilized for working the surface of a part typically comprise a plurality of cylindrical rollers or balls which contact the surface of the part with sufficient pressure to induce a compressive stress therein. Unfortunately, sharp surface demarcation typically exists along the boundaries of the burnished area often resulting in tensile residual stresses being formed along such boundaries. As disclosed herein, it has been found that gradually reducing the pressure being exerted by the burnishing member to reduce the magnitude of compression at the boundaries will reduce the build up of tensile residual stress. Further, it has been found that by controlling the compressive residual stress distribution and the magnitude of compression, the tensile stress distributions within a part may be offset or distributed in such a manner as to optimize the fatigue and/or stress corrosion performance of the part. Until now, however, a method and apparatus have not been developed that permitted the residual stress distributions and the magnitude of compression to be controlled in such a manner as to optimize fatigue performance for a specific applied stress distribution.

Consequently, a need exists for a relatively inexpensive, relatively time efficient method and apparatus for implementing the method for improving the physical properties of a part by inducing a layer of compressive stress in the surface of the part, which is effective for use with complex shaped surfaces, and which permits the magnitude of compression and the residual stress distributions to be produced on a surface to achieve optimum fatigue performance and stress corrosion performance of the part.

SUMMARY OF THE INVENTION

The novel method of the present invention for inducing a layer of compressive residual stress along the surface of a part comprises the steps of selecting a region of the part to be treated; selecting the magnitude of compression and the residual stress distribution to be induced in the surface of the selected region of the part; exerting pressure against the surface of the selected region, the pressure being applied in a selected pattern along the surface to form zones of defor-

3

mation having a deep layer of compressive stress; and varying the pressure being exerted against the surface to produce the desired residual stress distribution and magnitude of compression within the surface.

In another preferred embodiment of the invention, the step of exerting pressure against the surface of the selected region included performing a burnishing operation using a burnishing apparatus having a burnishing member for exerting pressure against the surface of the selected region of the part to produce a zone of deformation having a deep layer of compression.

In another preferred embodiment of the invention, the pressure being exerted on the surface of the part induces a deep layer of compression within the surface having associated cold working of less than about 5.0%.

In another preferred embodiment of the invention, the pressure being exerted on the surface of the part induces a deep layer of compression within the surface having associated cold working of less than about 3.5%.

In another preferred embodiment of the invention, whereby the step of exerting pressure on the surface of the part is performed by a burnishing operation using a burnishing apparatus having a burnishing member for exerting pressure against the surface of the selected region to induce a deep layer of compression within the surface having associated cold working of less than about 5.0 percent.

In another preferred embodiment of the invention, whereby the step of exerting pressure on the surface of the part is performed by a burnishing operation using a burnishing apparatus having a burnishing member for exerting pressure against the surface of the selected region to induce a deep layer of compression within the surface having associated cold working of less than about 3.5 percent.

In another preferred embodiment of the invention, whereby the selected pattern operates to vary the spacing between the zones of deformation to produce the desired residual stress distribution.

In another preferred embodiment of the invention, the step of selecting the magnitude of compression includes the step of programming a control unit to automatically adjust the pressure being exerted against the surface of the part.

In another preferred embodiment of the invention, the step of exerting pressure against the surface of the selected region includes performing a burnishing operation and the step of programming a control unit to control the direction of movement of a burnishing member to produce the desired stress distribution.

In another preferred embodiment of the present invention the step of varying the pressure being exerted against the surface of a part includes the steps of programming a control unit to adjust the pressure being exerted by a burnishing member against the surface of the part, and programming the control unit to direct the burnishing member over the part in a selected pattern to obtain the desired residual stress distribution.

In another preferred embodiment of the present invention, the step of varying the pressure being exerted against the surface of a part includes the step of gradually varying the magnitude of compressive stress in the areas immediately adjacent to the boundaries of the selected region.

In another preferred embodiment of the present invention, a method of inducing a layer of compressive stress in the surface of a part comprises the steps of inducing a deep layer of compression within the surface and inducing a more shallow layer of compressive stress within the surface of the selected region.

4

In another preferred embodiment of the present invention, a method of inducing a layer of compressive stress in the surface of a part comprises the steps of inducing a deep layer of compression within the surface and removing a layer of material along the surface being in low compression or tension.

In another preferred embodiment of the present invention, the method of inducing a layer of compressive stress in the surface of a part comprises the steps of programming a control unit to adjust the pressure being applied by the burnishing member against the surface of the part; programming the control unit to direct the burnishing member over the part in a predetermined pattern to induce a layer of compressive stress in the surface of the part; and applying a secondary process to impart a relatively shallow layer of compressive residual stress along the surface of the part to produce the desired residual stress distribution.

The novel apparatus for implementing the method of the present invention utilizes a burnishing process for inducing a layer of compressive residual stress having a preselected magnitude of compression and a desired stress distribution. In particular, the burnishing apparatus comprises a burnishing member for applying pressure against the surface of the selected region of the part to produce a zone of deformation having a deep layer of compression and a preselected magnitude within the surface. The burnishing apparatus further comprises means for moving the burnishing member in a predetermined pattern across the selected region to produce a desired residual stress distribution.

In another preferred embodiment of the invention the burnishing apparatus for implementing the burnishing method of the subject invention comprises a burnishing member for applying pressure against the surface of a part to induce a layer of compressive stress therein; means for adjusting the pressure being applied against the surface of the part by the burnishing member; and means for directing the burnishing member over the surface of the part in a predetermined pattern to provide the desired residual stress distribution.

In another preferred embodiment of the invention, the burnishing apparatus for implementing the burnishing method of the subject invention is coupled to a control unit for automatically controlling the movement, position, and application pressure of the burnishing member.

In another preferred embodiment of the invention, the burnishing apparatus for implementing the burnishing method of the subject invention comprises means for supplying a constant flow of fluid to support the burnishing member.

In another preferred embodiment of the invention, the burnishing apparatus for implementing the burnishing method of the subject invention comprises magnetic means for maintaining the burnishing member within the socket.

Another preferred embodiment of the invention is a blade for use in turbo machinery having a desired stress distribution.

Another preferred embodiment of the invention is a rotor disk for use in turbo machinery comprising selected regions having desired stress distributions.

Another preferred embodiment of the invention, a part selected from the group consisting of automotive parts, aircraft parts, marine parts, engine parts, motor parts, machine parts, drilling parts, construction parts, pump parts, and the like comprises regions of compressive residual stresses having predetermined stress distributions.

Another preferred embodiment of the invention, a part selected from the group consisting of automotive parts,

5

aircraft parts, marine parts, engine parts, motor parts, machine parts, drilling parts, construction parts, pump parts, and the like treated by the method comprising the step, or a combination of steps, of the present invention.

A primary object of this invention, therefore, is to provide a method and an apparatus for implementing the method of providing a part with an improved finish and with improved physical properties.

These and other objects and advantages of the invention will be apparent from the following description, the accompanying drawings and the appended claims.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a schematic block diagram illustrating the method of the present invention;

FIG. 2 is a graph illustrating the predicted longitudinal residual stress distribution, following 2.1% plastic strain, of a part having been treated by the method of shot peening and a part having been treated by the method of burnishing;

FIG. 3 is a graph illustrating the percent of cold work and yield strength distribution of a part having been treated by the method of shot peening and a part having been treated by the method of burnishing;

FIG. 4 is a schematic view of a generally rectangular region being treated by the method and apparatus of the invention for inducing a desired residual stress distribution and magnitude of compression whereby the pressure being exerted (force normal to the surface) against the surface is varied in two directions;

FIG. 5 is a schematic view of another region being treated by the method and apparatus of the invention for inducing a desired residual stress distribution and magnitude of compression whereby the density of the burnishing pattern is varied in the one direction;

FIG. 6 is a schematic view of another region being treated by the method and apparatus of the invention for inducing a desired residual stress distribution and magnitude of compression whereby the density of the burnishing pattern is varied in the two directions;

FIG. 7 is a schematic view of another region being treated by the method and apparatus of the invention for inducing a desired residual stress distribution and magnitude of compression, such as around a bolt hole, whereby the pattern is a symmetrical pattern;

FIG. 8 is a graph illustrating the residual stress distribution induced in the surface of a part in the direction of burnishing (parallel) and in the transverse direction (perpendicular);

FIG. 9 is a graph illustrating the percent cold work distribution for the burnishing operation shown in FIG. 8;

FIG. 10 is a diagrammatic view of the burnishing apparatus for implementing the method of the present invention;

FIG. 11 is a diagrammatic view of the socket of a preferred embodiment of the burnishing apparatus of the present invention showing magnetic means for maintaining the burnishing member within the socket;

FIG. 12 is a bottom diagrammatic view of the socket of FIG. 11 with the burnishing member removed;

FIG. 13 is a diagrammatic view of the socket of FIG. 11 showing the magnetic field lines for maintaining the burnishing member within the socket; and

FIG. 14 is a partial perspective view of a blade and a rotor disk of the present invention.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT

The present invention relates to a method and an apparatus for implementing the method of inducing a layer of

6

compressive residual stress along the surface of a part. In a preferred embodiment of the invention, as shown in FIG. 1, the method of the present invention comprises the steps of selecting a region of the part to be treated; selecting the magnitude of compression and the residual stress distribution to be induced along the surface of the selected region, such as for example by finite element analysis; and inducing a layer of compressive residual stress along the surface of the selected region having the desired magnitude of compression and stress distribution.

It has been found that for parts having a surface that has been substantially cold worked, such as a rotor disk for turbo machinery that has been treated by the process of shot peening, the cold worked compressive surface material typically not yield in tension, such as during high speed operation, while the lower yield strength interior material will yield. On unloading of the part, such as when the speed of revolution of the rotor disk slows, the surface of the part is driven into tension and will remain in tension, reducing the fatigue life, throughout the parts remaining life. Referring to FIG. 2, the inversion into tension of a surface of a part having been treated by the method of shot peening is shown compared to a surface of a part having been treated by the method of burnishing, each having a 2.1% plastic strain single cycle. Referring to FIG. 3, the corresponding percent of cold work and yield strength distribution are shown. As illustrated, upon unloading, the part that underwent the method of shot peening may actually invert from compression into a relative high level of tension, if a yield strength gradient exists, thereby significantly reducing the fatigue life of the part.

Accordingly, it has been found that the preferred method of the present invention for improving the surface finish, fatigue life, and stress corrosion resistance of a part is burnishing, whereby a rotary or sliding member is pressed against the surface of the part in order to compress the microscopic peaks in the surface into adjacent hollows. Such compression develops compressive stresses within the part by yielding the surface in tension so that it returns to a state of compression following deformation. As shown in U.S. Pat. No. 5,826,453, by the same inventor and incorporated herein by reference, by cold working the surface less than about 3.5%, and preferably less than about 2.0%, results in layer retention of compressive residual stress at elevated temperature, less rapid relaxation under cyclic loading, and minimizes the alteration of the residual stress field during tensile or compressive overload than conventional cold working and surface hardening processes. Accordingly, the method of the present invention is shown in FIG. 1 and preferably utilizes the process of burnishing to provide deep compression with a minimal amount of cold working and surface hardening. In particular, the region to be burnished along the surface of the part is first defined and a burnishing apparatus having a single-point of contact burnishing member is pressed against the surface of the part to create a zone of deformation producing a relatively deep layer of compression within the surface. The burnishing member is then passed in a predetermined pattern across the region. Preferably, the pattern of burnishing is such that the zones of deformation formed by each pass of the burnishing member do not overlap. As disclosed in U.S. Pat. No. 5,826,453, applying a single-pass, or multiple passes having a reduced compressive pressure, produces compressive residual stresses following tensile deformation of the surface having deep compression with minimal cold working.

In another preferred embodiment of the invention, the method further comprises the steps of determining the

7

optimum magnitude of compression to be induced at particular points along the surface of the selected region by controlling the pressure being exerted by the burnishing member. In another preferred embodiment of the invention, the method comprises the steps of varying the pattern of burnishing to produce a desired residual stress distribution. In another preferred embodiment of the invention, the method further comprises the steps of programming a control unit, such as a computer or numerical controller, to automatically regulate the burnishing force being applied to the burnishing member thereby controlling the pressure being exerted against the surface of the part and the corresponding magnitude of compression being induced by the burnishing apparatus. The control unit may also be programmed to control the direction of movement of the burnishing apparatus to produce the desired residual stress distribution.

The particular pressure and the pattern of burnishing for a part may be selected whereby the magnitude of compression and the residual stress distribution optimizes the fatigue performance of the part. For illustration, as shown in FIG. 4, a rectangular burnishing region is selected and the burnishing member is pressed against the surface of the part in a particular (raster) pattern, as shown by the arrow indicating the path of the burnishing member. The normal force (F_z) being applied to the burnishing member is varied to increase or decrease the pressure being exerted against the surface of the part. While FIG. 4 shows a linear variation in the normal force and the corresponding pressure being applied against the surface, parallel (X-direction) and perpendicular (Y-direction) to the direction of burnishing, it should now be apparent to those skilled in the art that the pattern of burnishing and the form and rate of reduction or increase in pressure being exerted against the surface can be controlled to provide a wide variety of residual stress distributions and magnitude of compression.

Referring to FIG. 5, another illustration of the method of the present invention is shown whereby variations in residual stress distribution may also be achieved by varying the pattern of burnishing, independently or in conjunction with variations in burnishing pressure. As shown, the spacing along the X-direction, perpendicular to the direction of travel of the burnishing member, has been varied to increase and decrease the spacing between each pass of the burnishing member thereby changing the density (D_x) of burnishing. As shown, the spacing between each pass of the burnishing member varies linearly, however, it should now be apparent to those skilled in the art that other burnishing patterns may be selected to produce the desired residual stress distribution.

Referring to FIG. 6, another pattern of burnishing is shown whereby the spacing density (D_x) is varied in two dimensions (X and Y directions) as a function of the length of the burnishing pass, in order to produce the desired stress distribution for the part being burnished.

Referring to FIG. 7, another pattern of burnishing is shown whereby a region is designated and the magnitude of compression and the residual stress distribution is selected that optimizes the fatigue performance of the part. As shown, the residual stress distribution has a symmetrical pattern such as what would be preferred for use around bolt holes or for "feathering" in a state of compressive stress in the fillet area of a rotor disk. It should now be apparent to those skilled in the art that the burnishing pressure, the density of burnishing, and the pattern of burnishing can be varied to produce the desired residual stress distribution and magnitude of compression for a part for a specific engineering application.

8

In another preferred embodiment of the invention, the method of inducing a layer of compressive residual stress along the surface of a part includes the step of using a secondary process, such as shot peening, grit blasting, tumbling or other similar abrasive impact processes to induce a shallow layer of compressive residual stress near the surface of the part following burnishing. As shown in FIGS. 8 and 9, burnishing of a surface inherently produces a Hertzian loading of the surface resulting in maximum compression beneath the surface of the work piece. The residual stress at the surface can be near zero or even tensile, and is a function of the direction of the burnishing operation. The surface residual stress is typically less compressive in the direction of burnishing (parallel) than in the transverse direction (perpendicular) due to the effect of displacement of material laterally during passage of the burnishing member. The presence of lower compression at the surface has been found to allow the initiation of fatigue cracks at the surface of the part. Although these cracks are arrested as they propagate deeper into the more highly compressive material, the presence of surface cracks and the stress intensity factor associated with them is highly undesirable. It has been found that the method of this invention comprising the steps of burnishing a part in combination with the secondary process identified herein above provides surface compression as well as deep compression resulting in a part having superior resistance to surface crack initiation and propagation. In another embodiment of the invention, the method of the present invention comprises the step, in conjunction with the first step of burnishing, of removing a layer of low compression by electropolishing, etching or other similar means that will not induce a state of stress or through mechanical means, such as low stress grinding, polishing, tumbling, or other such means, which will induce a state of shallow compressive stress.

Referring to FIG. 10, a preferred embodiment of the burnishing apparatus 100 for implementing the burnishing method of the subject invention is shown comprising a generally cylindrical socket 102 which conventionally mounts to a support 104 of any particular description typically used for supporting burnishing tools which is attached to a conventional machine tool fixture (not shown). In a preferred embodiment of the invention, the support 104 is coupled to the socket 102 and provides means for imparting a normal force F to a burnishing member 106 to effect the proper burnishing pressure sufficient to deform the surface 108 of the part 110.

The socket 102 includes a seat 112 adapted to the surface of the burnishing member 106 which is disposed within the seat 112, and an inner chamber 114. The size of the seat 112 is determined by the size and shape of the burnishing member 106 and is selected to provide a small clearance 116 between the seat 112 and the burnishing member 106. As shown, the support 104, in cooperation with the machine tool fixture, is adapted for controlling the movement of the socket 102 and includes means for forcing the socket 102 and the burnishing member 106 against the surface 108 of the part 110 being burnished. Without departing from the invention, it should now be apparent to those skilled in the art that various apparatus may be constructed to allow the socket to be moved to various positions or to allow the part being treated to rotate or pass in contact with the burnishing member in such a way that the selected region is burnished using the method of the present invention.

The socket 102 is further provided with a fluid passage 118 in flow communication with the seat 112 and extends from the seat 112 through the inner chamber 114 to a fitting

(not shown) for connecting to a positive displacement pump **120** for providing a constant volumetric flow of fluid from a fluid supply **122** to the seat **112**. The fluid supply **122** may be an external supply (not shown) or may be in the form of a sump **124**, as shown, thereby forming a closed-loop fluid system. The positive displacement pump **120** is preferably coupled to a direct current (DC) electric motor **126** and a fast acting motor speed control **128**. The motor speed control **128** functions to maintain a constant angular velocity of the motor **126** to sustain the constant volumetric fluid flow to the socket **102** regardless of any changes in fluid pressure. A pressure sensor **130**, such as a pressure transducer, is connected to the fluid passage **118** for monitoring fluid pressure and is coupled to a control unit **132**, such as a computer or a numerical controller, which is also coupled to either a position regulator **134**, such as a spring, or a pressure regulator **136**, such as a hydraulic or pneumatic system, that operate with the burnishing member **106** to provide the proper burnishing pressure being exerted against the surface **108** of the part **110**.

To understand how the elements of this invention described are interrelated, the operation of the burnishing apparatus **100** will now be described. During operation, fluid, such as a lubricating fluid, is fed under pressure from the fluid supply **122** by use of the positive displacement pump **120** through the fluid passage **118** and into the inner chamber **114**. The fluid in the inner chamber **114** is then fed under pressure around the burnishing member **106** through clearance **116** to force the burnishing member **106** outwardly. The lubricating fluid flows around the outer surface of the burnishing member **106** to permit the burnishing member **106** to float continuously upon a thin film of fluid. The socket **102** is then advanced towards the surface **108** of the part **110** by operation of the support and the machine tool fixture (not shown) until the forward most portion of the burnishing member **106** makes contact with the surface **108**. By further adjusting the speed of the motor, a desired amount of lubrication fluid will flow around the burnishing member **106** and be transferred onto the surface **108** of the part **110** to provide the desired lubrication and cooling for the burnishing operation. During burnishing, the further most portion of the burnishing member **106** contacts the surface **108** of the part **110** causing the burnishing member **106** to move inwardly into the socket **102** thereby reducing the clearance **116** between the burnishing member **106** and the socket **102** thereby increasing the pressure of the fluid in the fluid passage **118**. The increase in fluid pressure is detected by the pressure sensor **130** which is coupled to the control unit **132** that functions to adjust the force **F** being applied to the burnishing member **106** to maintain a constant or controlled variable burnishing pressure against the surface **108**. It should now be apparent to those skilled in the art that the constant flow burnishing apparatus **100** of the present invention, unlike conventional constant pressure burnishing apparatus that follow the surface topography of the part, automatically increases the force **F** being applied to the burnishing member **106**, and the corresponding pressure being exerted against the surface **108**, on high points and decreases on low points along the surface **108**. Accordingly, the pressure or the compressive force exerted on the surface **108** of the part **110** by the burnishing member **106** can be precisely regulated to provide optimum surface finish and uniform burnishing of the part.

In a preferred embodiment of the invention, the proper pressure or compressive force to be applied to the surface **108** of the part **110** during the burnishing operation is provided by using the position regulator **134** whereby the

force **F** being applied to the burnishing member **106** is a function of the position of the socket **102**. As shown, the position regulator **134** includes a spring means **140**, such as a coil spring, deflection members, or Belleville washers, having a known spring characteristic, which compresses or expands axially to apply a given normal force **F** to the burnishing member **106**. Because the burnishing member **106** is coupled through the spring means **140**, the force **F** being applied to the burnishing member **106** and the resulting pressure being exerted on the surface **108** of the part **110** can be accurately controlled by positioning (moving) the socket **102** using the conventional machine tool fixture (not shown). The control unit **132** operates with a feed back signal from the pressure sensor **130** to achieve closed loop control of the force **F** and the corresponding pressure being exerted on the surface by the burnishing member **106**.

Preferably the machine tool fixture supporting the socket **102** is a "three-axis" machine that provides for linear motion along mutually orthogonal axis of a fixed coordinate system.

It should now be apparent to those skilled in the art that by using a programmable control unit **132** which is configured to continuously track the position of the burnishing member **106**, the socket **102** can be accurately positioned and moved in a selected pattern. Further, in combination with passing the burnishing member is a selected pattern across the surface of the part, the pressure being exerted against the surface may be varied to obtain a region having the desired residual stress distribution and magnitude of compression.

In another preferred embodiment of the invention, the proper pressure or compressive force to be applied to the surface **108** of the part **110** during the burnishing operation is provided by use of the pressure regulator **136**. As shown in FIG. **10**, the pressure regulator **136** comprises a source of pressurized fluid **141** for providing pneumatic or hydraulic pressure against a piston **142**, diaphragm or other similar means. The piston **142** is coupled to the burnishing member **106** in such a manner that movement of the piston **142** operates to increase or decrease the force **F** being applied to the burnishing member **106** thereby increasing or decreasing the corresponding pressure being exerted by the burnishing member **106** on the surface **108** of the part **110**. In operation, for constant pressure burnishing, the machine tool fixture moves the socket **102** in a predetermined pattern along the surface **108** of the part **110**. The control unit **132** functions with a feed back signal from the pressure sensor **130** to achieve closed loop control of the force **F** and the corresponding pressure being exerted on the surface **108** by the burnishing member **106**. It should now be apparent to those skilled in the art that by using the control unit **132**, the burnishing member **106** can be accurately moved in a selected pattern while exerting a predetermined pressure against the surface **108** of the part **110** to obtain a region having the desired residual stress distribution and magnitude of compression.

Conventional constant pressure burnishing apparatus require a containment means, such as end caps, for maintaining the burnishing member within the apparatus. The containment means must be capable of withstanding high pressure and forces, including the time when the burnishing member is not in contact with the surface of the part. In the event that the containment means fails, the burnishing member could be propelled from the burnishing apparatus at high velocity. In contrast, the constant flow burnishing apparatus of the subject invention eliminates the need of a containment means that is capable of withstanding high pressure.

11

Referring to FIGS. 11, 12 and 13, the burnishing member 106 may be selected from various materials having a higher yield strength than the part 110 being burnished and having a relatively high elastic modulus to allow maximal deformation of the part 110. In a preferred embodiment of the invention, the burnishing member 106 is formed from a high carbon steel or a sintered tungsten carbide containing a portion of a cobalt binder. The inner chamber 114 of the socket 102 is shown having a magnetic means 144, such as a permanent magnet or an electric magnet or the like, which produce magnetic flux 145 (FIG. 13) that functions to maintain the burnishing member 106 within the seat 112. It has been found that forming the socket 102 from a ferromagnetic alloy, such as a martensitic stainless steel AISI 440C, the socket 102 functions as a pole piece thereby increasing the holding power of the magnet means 144. Because the bearing member 106 is supported by a low volume of fluid having a constant flow rate, the bearing member 106 will be retained within the socket 102 even while the fluid is flowing and the socket 102 is being repositioned or moved out of contact with the surface 108 of the part 110.

Referring to FIG. 14, a blade of the present invention is shown, for use in turbo machinery. The blade 146 includes a generally rectangular platform 148; an elongated airfoil 149 having a leading edge 150 and a trailing edge 152, the airfoil 149 being rigidly attached to and extending radially outwardly from the platform 148; and a root 154 rigidly connected to and extending radially inwardly from the platform 148 having a dovetail portion 155 for mounting to a rotor disk 156. As used herein, the term "outwardly" refers to the direction away from the center of rotation of the blade and rotor disk and the term "inwardly" refers to the direction towards the center of rotation of the blade and rotor disk. The rotor disk 156 includes a plurality of circumferentially spaced axially disposed slots 158 therein. The blade 146 is attached to the rotor disk 156 by inserting the root 154 into a slot 158. As shown, the root 154 and the slot 158 have complementing surfaces for securing the blade 146 to the rotor disk 156. During operation, the rotor disk 156 and the attached blades 146 are subjected to high centrifugal loads that produce high dynamic stresses that may cause high cycle fatigue along portions of the rotor disk 156 and each blade 146. Further, the leading edge 150 of the blade 146 is often subjected to damage by the impact of foreign objects in the fluid stream.

In a preferred embodiment of the invention, the blade 146 is treated by the method comprising a step or a combination of steps disclosed herein. In another preferred embodiment of the invention, the rotor disk 156 is treated by the method comprising a step or a combination of steps disclosed herein.

Another preferred embodiment of the invention, a part is selected from the group comprising automotive parts, aircraft parts, marine parts, engine parts, motor parts, machine parts, drilling parts, construction parts, pump parts, and the like treated by the method comprising the step, or a combination of steps, of the present invention.

The method and apparatus for implementing the method of the subject invention utilizes a burnishing method that produces cold work and surface work hardening far less than either conventional shot peening, gravity peening, and conventional burnishing or deep rolling methods. The increase in residual compressive stress with minimal cold work developed by the subject invention penetrates to a greater depth than most conventional methods, such as shot peening and results in longer retention of compressive residual stress at elevated temperature, less rapid relaxation under cyclic

12

loading, and minimizes the alteration of the residual stress field during tensile or compressive overload than conventional cold working and surface hardening processes. Further, the method for inducing a layer of compressive residual stress along the surface of a part and the apparatus for implementing the method provides control of the particular stress distribution and magnitude of compression that optimizes the fatigue performance of the part. By controlling the pattern of burnishing and by gradually reducing the magnitude of compression near the boundaries of the regions being burnished ("feathering"), the tensile zones which occur immediately adjacent and parallel to the boundaries may be reduced or eliminated.

Accordingly, the method and apparatus for implementing the method of the subject invention provides a relatively inexpensive and effective means of providing a compression force on a workpiece to induce compressive residual stress in a well defined localized region of a simple or complex part surface configuration with a minimum of cold working and surface hardening. By minimizing the amount of cold working and surface hardening, the method of the subject invention produces longer retention of compressive residual stress at elevated temperature, less relaxation under cyclic loading, and minimizes the alteration of the residual stress field during tensile or compressive overload. Further, the method and the apparatus of the invention for inducing a layer of compressive residual stress along the surface of the part permits a variety of burnishing patterns to be designated to produce regions of residual stress that are appropriate for a specific engineering application. In addition, a part treated using the method of the invention have improved stress corrosion cracking resistance.

While the method and apparatus described constitute preferred embodiments of the invention, it is to be understood that the invention is not limited to the precise method and apparatus, and that changes may be made therein without departing from the scope of the invention which is defined in the appended claims.

What is claimed is:

1. A method of inducing compression along the surface of a part comprising the steps of:

- selecting a region of the part to be treated;
- selecting the magnitude of compression to be induced along the surface of the selected region;
- exerting pressure against the surface of the selected region using an apparatus having a member for exerting the pressure against the surface of the selected region and a socket for receiving the member; and

supplying a constant volume flow of fluid to the socket such that test fluid flows over the member.

2. The method of claim 1 whereby the pressure being exerted against the surface of the part is performed by a burnishing operation.

3. The method of claim 1 wherein said pressure being exerted on the surface of the part induces a deep layer of compression within the surface having associated cold working of less than about 5.0 percent.

4. The method of claim 1 wherein said pressure being exerted on the surface of the part induces a deep layer of compression within the surface having associated cold working of less than about 3.5 percent.

5. The method of claim 1 further wherein the step of selecting the magnitude of compression includes the step of programming a control unit to automatically adjust the magnitude of compression being induced within the surface of the part.

13

6. The method of claim 1 wherein a selected pattern is selected along the surface varies such that is the spacing between the zones of deformation.

7. The method of claim 1 wherein the step of exerting pressure against the surface of the selected region includes the step of programming a control unit to control the application of said pressure.

8. The method of claim 1 further includes varying the pressure being exerted against the surface and inducing a more shallow layer of compressive stress within the surface of the part.

9. The method of claim 1 further comprising the step of removing a layer of material along the surface being in low compression or tension.

10. The method of claim 1 wherein the part is selected from the group consisting of automotive parts, aircraft parts, marine parts, engine parts, motor parts, machine parts, drilling parts, construction parts, pump parts, and parts for use in turbo-machinery.

11. A method of inducing a layer of compressive stress in the surface of a part comprising the steps of:

selecting a region of the part to be treated;

selecting the magnitude of compression and the residual stress distribution to be induced in the surface of the selected region;

programming a control unit to pass a burnishing member positioned within an inner chamber of a burnishing apparatus over the selected region in the selected pattern to produce a zone of deformation having a deep layer of compression within the surface;

programming the control unit to increase, decrease or maintain the pressure being exerted against the surface at selected points along the selected pattern and to vary the rate of increase and decrease of pressure to obtain the desired residual stress distribution and magnitude of compression within the surface; and

supplying a constant volume flow of fluid to the inner chamber such that the fluid supports the burnishing member.

12. The method of claim 11 wherein said pressure being exerted on the surface of the part induces a deep layer of compression within the surface having associated cold working of less than about 5.0 percent.

13. The method of claim 11 wherein said pressure being exerted on the surface of the part induces a deep layer of compression within the surface having associated cold working of less than about 3.5 percent.

14. The method of claim 11 wherein the burnishing apparatus comprises means for automatically adjusting the pressure being exerted against the surface of the selected region to increase on the high points and decreases on the low points encountered by the burnishing member along the surface of the part.

15. A method of inducing a layer of compressive stress in the surface of a part comprising the steps of:

selecting a region of the part to be treated;

selecting the magnitude of compression and the residual stress distribution to be induced in the surface of the selected region;

14

programming a control unit of a burnishing apparatus to perform a burnishing operation, the burnishing operation being performed along the selected region in a selected pattern to produce a zone of deformation having a deep layer of compression within the surface having associated cold working of less than about 5.0 percent;

performing a second operation to induce a more shallow layer of compressive stress within the surface of the part to produce the desired stress distribution;

whereby said burnishing apparatus further comprising an inner chamber for receiving a burnishing member, means for supplying a constant volume flow of fluid into the inner chamber such that the fluid flows supports the burnishing member, and means for automatically adjusting the pressure being exerted against the surface of the selected region that increases on the high points and decreases on the low points that are encountered along the surface of the part during the burnishing operation.

16. A burnishing apparatus for inducing a compressive stress in the surface of a part comprising:

a burnishing member;

a socket having an inner chamber and a seat for receiving said burnishing member;

means for applying a force against said burnishing member for exerting pressure against the surface of the part; and

means for providing a constant volume of fluid to said inner chamber;

wherein said socket provides a clearance between said seat and said burnishing member for permitting the fluid to pass.

17. The burnishing apparatus of claim 16 further comprising:

a pressure sensor for monitoring the fluid pressure; and

means for adjusting the force being applied against the burnishing member and the corresponding pressure being exerted by said burnishing member against the surface in response to the fluid pressure.

18. The burnishing apparatus of claim 16 further comprising:

a programmable control means configured to continuously track the position of the burnishing member and for automatically adjusting the force being applied against the burnishing member and the corresponding pressure being applied against the surface by said burnishing member.

19. The burnishing apparatus of claim 16 further comprising:

a programmable control means configured to direct the motion of said burnishing member in a selected pattern across the surface of a part.

* * * * *

UNITED STATES PATENT AND TRADEMARK OFFICE
CERTIFICATE OF CORRECTION

PATENT NO. : 6,415,486 B1
DATED : July 9, 2002
INVENTOR(S) : Paul S. Prevey, III

Page 1 of 1

It is certified that error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:

Column 12,

Line 51, "test" should be changed to -- the --.

Signed and Sealed this

Fifth Day of November, 2002

Attest:

A handwritten signature in black ink, appearing to read "James E. Rogan", written over a horizontal line.

Attesting Officer

JAMES E. ROGAN
Director of the United States Patent and Trademark Office